



NORDIC COLLECTION

0945 | FABRICS

Technical Specifications

Roll Width	140cm (+/- 3%)	
Average Roll Length	40	
Weight	505 g/ml (+/- 5%)	
Surface Composition	100% Polyester	
Backing Composition	100% Polyester	
Abrasion Test		
EN ISO 12947-1,2	>65.000	
Pilling		
EN ISO 12945-2	4	
Colour Fastness to Artificial Light		
EN ISO 105-B02, Method 2 - Exposure level 6	>5	
Seam Slippage Resistance	Warp	Weft
EN ISO 13936-2	2,00 mm	2,00 mm
Colour Fastness to Rubbing	Dry	Wet
EN ISO 105-X12	4-5	4-5
Tensile Strength	Warp	Weft
EN ISO 13934-1	1000 N	910 N
Tear Growth Resistance	Warp	Weft
EN ISO 13937-3	140,0 N	260,0 N
Electrostatic Behaviour		
DIN 54345-1:1992-02	No antistatic	



ADVANCED
FABRICS



HOME FABRICS

Applications and Features



Anti-stain

EN ISO 4920:2012-12



Cigarette Resistant

EN 1021-1

BS 5852 Part 1 Source 0



Respects the environment using application of new technologies in the production process



STANDARD
100
9342CIT
CITEVE

- Frequent wash may affect the performance of the product or its treatment (when present)
- Any stain, spills or soiling should be cleaned up promptly with a 5% neutral soap solution using a clean cloth, gently pressed and rubbing in smooth circular movements.
- In case of dry soil please remove first with a vacuum cleaner
- For articles with the Easy-to-Clean feature we recommend using a 100% cotton cloth and a soft brush if necessary
- We do not accept responsibility for any damage resulting from inappropriate use, chemical cleaning or additional impregnation.
- The analytical results are referred only to the sample tested.
- Discoloration and colour deviations tolerated by permissible industrial standards do not constitute reasons for claims.
- Colour migration may occur.
- Pilling is a natural phenomenon that occurs due to daily use and frequent washing and cannot be avoided.
- Dry cleaning is recommended to preserve the FR treatment performance.
- We reserve the right to modify, at any moment and without notice any product specifications.

