

WILDE

GENERAL SPECIFICATIONS

Width	54"
Weight	20 oz/linear yard
Surface Composition	100% Polyurethane (Polycarbonate)
Substrate Composition	75% Polyester, 25% Cotton
Gauge	0.040
Thickness	1.00 mm

FLAME RETARDANCY SPECIFICATIONS

CAL-TB 117-2013	Passes
NFPA 260	Passes
UFAC Class 1	Passes

REDUCED ENVIRONMENTAL IMPACT

No added Flame Retardant Chemicals

No added Anti-Microbial/Anti-Bacterial Chemicals

PVC Free

Phthalate Free

Lead Free/Heavy Metal Free

BPA Free/TRIS Free/Formaldehyde Free

Does not contain Conflict Minerals

CAB 2998 Compliant

PERFORMANCE SPECIFICATIONS

Abrasion	165,000+ DR
Colorfastness to Crocking	Wet: 5 Dry: 5
Seam Slippage	Fill: 87.9 Warp: 88.7
Tensile Strength	Fill: 106 Warp: 128
Tear Strength: Tongue Tear	Fill: 7.6 Warp: 11.3
Hydrolysis	7 weeks
Anti-Bacterial, Anti-Microbial, Mildew Resistant, Denim Dye Resistant	Passes
Cold Crack	-20°
Colorfastness to Light	200 Hours
Bleach Resistant	Yes - 20% Dilution

RECOMMENDED APPLICATIONS



*ACT® Registered Certification Marks

FINISHES

WILDE

CARE & CLEANING GUIDE

Prompt cleaning is always recommended. Recommended cleaning steps are listed by type of stain.

Regular Cleaning & Maintenance

Clean the soiled area with mild soap and water, then rinse with fresh water and wipe dry with a clean cloth.

Dirt
Grime

Food Stains/Oils

Wipe the affected area with a soft cloth with appropriate pressure. If some stain persists, clean with mild soap and water. Rinse with fresh water and wipe dry.

Mustard
Ketchup
Chocolate
Coffee/Tea
Salad Dressing

Healthcare/Disinfection

Wipe the affected area with a soft cloth with appropriate pressure. If some stain persists, spray it with a 70% dilution of isopropyl alcohol and water and wipe. Rinse with fresh water and wipe dry.

Blood
Urine
Betadine

Ink Marks/Graffiti

Rub the affected area with a dry soft cloth with firm pressure. If some stain is still present spray it with a 70% dilution of isopropyl alcohol and water and wipe. Rinse with fresh water and wipe dry.

Ballpoint Pen
Permanent Marker

Denim Dye Transfer

This material is designed to withstand the transfer of most types of Indigo Dye. In the case that faint dye transfer is visible, this can typically be removed with a 70% dilution of isopropyl alcohol and water.

Blue Jeans